



BANDIRMA MERMER Sanayi Ticaret A.Ş.

APPLIED STANDARD : TS EN 1469 ,TS EN 12058 (TS EN 1936, EN 1936, EN 12524 ,EN 12524, EN 13755, EN 12371, EN 14066 EN 12372, EN 14579, EN 1925, EN 14231, EN 14157)

PRODUCT : Olive Maron

TS 5994 EN 12670

PETROGRAPHIC NAME : Dolomitic Limestone

ORIGIN : KARACABEY/BURSA

AREA OF USAGE : OUTDOOR, INDOOR

PRODUCER NAME&ADDRESS : BANDIRMA MERMER Sanayi Ticaret A.Ş. / Balıkesir Asfaltı 9.Km No:418 Bandırma/BALIKESİR

Characteristics	Declaration	Test Method
Reaction to fire	A1 class	Without Test (as amending 96/603/EC)
Apparent density	2732 ± 3,6 kg/m ³	EN 1936
Open porosity	% 0,238 ± 0,03	EN 1936
Thermal conductivity (λ)	2,58 W/m.k	EN 12524
Water vapour resistance factor (dry)	286 μ-value	EN 12524
Water absorption at atmospheric pressure	% 0,087 ± 0,01	EN 13755
Frost resistance (-)	% 7,63	EN 12371
Resistance to ageing by thermal shock By weight (-) By modulus of elasticity (-)	% 0,015 % 3,88	EN 14066
Flexural strength under concentrated load	16,34 ± 0,9 MPa	EN 12372
P-wave velocity	6538 ± 41 m/s	EN 14579
Water absorption coefficient by capillarity	0,161 ± 0,07 g/m ² .s ^{0.5}	EN 1925
Resistance against sliding	SRV (dry) : 34 SRV (wet) : 8	EN 14231
Abrasion strength (method-B/Bohme)	11,22 ± 0,05 cm ³ /50 cm ²	EN 14157
Weavability	On the surface, there is no trace of pollution will create visually.	Visually

BANDIRMA MERMER Sanayi Ticaret A.Ş.